

AD-A051 423

ARMY INST OF DENTAL RESEARCH WASHINGTON D C  
STRESS RELAXATION OF HIGH-COPPER AMALGAM ALLOYS, (U)  
MAR 78 E F HUGET, L B DE SIMON, S G FEHRMAN

F/G 11/6

UNCLASSIFIED

NL


1 OF 1  
ADA  
051423




END  
DATE  
FILMED

4 -78

DDC





NATIONAL BUREAU OF STANDARDS  
MICROCOPY RESOLUTION TEST CHART

REPORT DOCUMENTATION PAGE

READ INSTRUCTIONS  
BEFORE COMPLETING FORM

1. REPORT NUMBER	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) Stress Relaxation of High-Copper Amalgam Alloys		5. TYPE OF REPORT & PERIOD COVERED Manuscript
6. PERFORMING ORG. REPORT NUMBER		
7. AUTHOR(s) Eugene F. Huget, <del>MAJ, DC</del> ; Laszlo B. de Simon, Steven G. Fehrman, <del>MAJ, DC</del> and Stanley G. Vermilyea, MAJ, DC		8. CONTRACT OR GRANT NUMBER(s) NA
9. PERFORMING ORGANIZATION NAME AND ADDRESS Division of Dental Materials U.S. Army Institute of Dental Research Washington, D.C. 20012		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS DA OG 6033 00-119-8
11. CONTROLLING OFFICE NAME AND ADDRESS U.S. Army Institute of Dental Research Walter Reed Army Medical Center Washington, D.C. 20012		12. REPORT DATE 11 10 March 1978
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		13. NUMBER OF PAGES 10 12 13 p.
		15. SECURITY CLASS. (of this report) Unclassified
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Unlimited		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Amalgam alloys; high-copper amalgam alloys; viscoelastic properties and stress relaxation.		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) Stress relaxation of seven high-copper dental amalgam alloys was studied over the temperature range of 0 to 55C. At each test temperature the alloy containing the most copper (30 percent) exhibited the lowest rate and lowest magnitude of stress loss. Stress losses and relaxation rates of all materials increased with temperature. However, patterns of stress decay could be correlated with neither the compositional nor the structural characteristics of the individual alloys. Stress relaxation behavior may be an indicator of the relative performance capabilities of high-copper amalgams.		

038 670

JOB

ADA051423

WUB FILE COPY

DDC  
MAR 20 1978  
F

# STRESS RELAXATION OF HIGH-COPPER AMALGAM ALLOYS

Eugene F. Huget \*  
Laszlo B. de Simon \*\*  
Steven G. Fehrman \*\*\*  
Stanley G. Vermilyea \*\*\*\*

U.S. Army Institute of Dental Research

Washington, D.C. 20012

Commercial materials and equipment are identified in this report to specify the experimental procedure. Such identification does not imply recommendation or indorsement or that the equipment and materials are necessarily the best available for the purpose.

- \* Lieutenant Colonel, Dental Corps, U.S. Army, Chief, Division of Dental Materials.
- \*\* Physical Scientist.
- \*\*\* 2LT, Medical Service Corps, Biomedical Engineer.
- \*\*\*\* Major, Dental Corps, Research Dental Officer.

Since the late 1960's interest in the viscoelastic behavior of hardened dental amalgam has grown markedly. Accordingly, a number of investigators<sup>1-3</sup> have demonstrated the usefulness of laboratory creep data in estimating the clinical performance capabilities of various dental alloys.

In addition to steady state creep, a progressive increase in deformation under constant load, amalgam alloys exhibit other time-dependent characteristics. One such characteristic is stress relaxation,<sup>4,5</sup> a gradual decrease in stress under a constant strain.

Short term stress relaxation behavior of two lathe cut alloys, a spherical alloy of conventional composition, and a material which contained a silver-copper dispersant was examined in a previous study.<sup>5</sup> Comparatively, stress losses and rates of stress decay for the lathe cut alloys were significantly higher than those of the other two materials. The findings suggested that particle morphology and composition affect the stress relaxation of dental amalgam.

The present investigation was conducted to study the stress relaxation behavior of additional relatively new high-copper amalgam alloys (copper content >6 percent).

#### Materials and Methods

Test materials included two spherical ternary alloys (A.\*

\* Sybraloy, Kerr Sybron Corp., Romulus, MI 48174.

ACCESSION for	
NTIS	White Section <input checked="" type="checkbox"/>
DDC	B.f. Section <input type="checkbox"/>
UNANNOUNCED	<input type="checkbox"/>
JUSTIFICATION	
BY	
DISTRIBUTION/AVAILABILITY CODES	
Dist.	SPECIAL
A	

copper 30% and B,<sup>+</sup> copper 12%), a spheroidal ternary alloy (C,<sup>#</sup> copper 13%), a spheroidal quaternary alloy (D,<sup>§</sup> copper 13% and Indium 5%), two products formulated from mixtures of fine cut filings of conventional composition and copper-containing spherical particles (E,<sup>¶</sup> copper 9% and F,<sup>Ω</sup> copper 12%) and an alloy composed of an admixture of rounded particles and spheres (G,<sup>Π</sup> copper 21%).

Amalgamates of all materials were made with the use of a mechanical device.<sup>\*\*</sup> Mercury-alloy portions and trituration times are given in the appendix.

The amalgams were condensed in 4 mm X 8 mm-steel molds by the all-mechanical procedure prescribed by American Dental Association Specification No. 1.<sup>6</sup> The specimens were aged for seven days at 37C and 100 percent relative humidity. The ends of the hardened test pieces were ground flat and perpendicular to their axes.

----

+ Tytin, S. S. White Co., Philadelphia, PA 19162.

# Aristaloy CR, Baker Dental, Carteret, NY 07008.

§ Indiloy, Shofu Dental Corp., Menlo Park, CA 94025.

¶ Optaloy II, L. D. Caulk Co., Milford, DE 19963.

Ω Dispersalloy, Johnson & Johnson, East Windsor, NJ 08520.

Π Cupralloy, Weber Consumable Products, Mount Vernon, NY 10533.

\*\* Wig-L-Bug, Crescent Dental Mfg. Co., Lyons, IL 60534.

The test procedure was designed to measure stress relaxation of the alloys at nominal temperatures of 0, 10, 20, 30, 37, 42, 48 and 55C. The amalgam cylinders were immersed in a water bath and conditioned for 15 minutes at the desired test temperature. Six specimen-lots of each alloy were tested within the bath at each of the aforementioned temperatures. Each cylinder was compressed axially on a constant strain-rate testing machine.<sup>++</sup> Crosshead speed of the machine was 0.02 inch/min. When a stress ( $S_o$ ) of 28 MN/m<sup>2</sup> was reached, descent of the crosshead was stopped. Relaxation of the loaded specimens yielded a measurable stress loss ( $D_t$ ) with no change in strain. Stress relaxation ( $D_t$ ) was measured at 6 second intervals over a period of 60 seconds. To compensate for the inherent relaxation of the testing machine, a 4 mm X 8 mm cylinder of stainless steel was subjected to the compression procedure before and after the testing of three amalgam specimens. The resulting system relaxation pattern was used in adjusting the experimental data. An illustration of the compression-relaxation sequence can be found in an earlier report.<sup>5</sup>

#### Results

Fractional stress-loss ( $D_t/S_o$ ) patterns of the high-copper alloys at one test temperature (37C) are shown in Figure 1. Fractional stress losses did not increase linearly over the 60-second period of observation. However, all curves representing the behavior of the alloys at each of the eight experimental temperatures become linear when plotted against  $\ln(\text{time} + 1)$ . Relaxation rates with reference to  $\ln$

----

<sup>++</sup> Instron Universal Testing Machine, Instron Corp., Canton, MA 02021.

(time + 1) were defined by the slopes of these lines. Relative relaxation rates for the alloys over the entire experimental temperature range are shown in Figure 2. Relaxation rates for materials A, D and E varied exponentially with temperature. Curves depicting the relative relaxation rates of the other alloys were complex. Relaxation rates of alloys B, C, F and G increased exponentially with temperatures ranging from 0 to 48C. The relaxation rates of the latter four materials appeared to be constant between 48 and 55C.

Mean values for total stress loss at 60 seconds ( $D_t/S_o/60$ ) are given in Table 1. Over the 0 to 55C temperature range, alloy E exhibited the greatest increase in stress decay (10 to 56 percent); alloy A showed the least increase (5 to 21 percent).

#### Discussion

From the available data, the extent to which any single factor affects the stress relaxation of the high-copper amalgams cannot be ascertained. It would appear, however, that the viscoelastic behavior of each alloy is a manifestation of the interaction of unique compositional, metallurgical and physical features.

It is common practice to study the rheological properties of dental amalgam at or near normal mouth temperature (37C). However, in function an amalgam restoration is subjected not only to a broad range of temperatures but also to rapid cyclic temperature change. The materials considered in the present study exhibit differences with respect to the effect of temperature on relaxation behavior.

The recent findings suggest that among the alloys, subtle differences in clinical performance potential may exist.

#### Summary

Stress relaxation of seven high-copper dental amalgam alloys was studied over the temperature range of 0 to 55C. At each test temperature the alloy containing the most copper (30 percent) exhibited the lowest rate and lowest magnitude of stress loss.

Stress losses and relaxation rates of all materials increased with temperature. However, patterns of stress decay could be correlated with neither the compositional nor the structural characteristics of the individual alloys.

Stress relaxation behavior may be an indicator of the relative performance capabilities of high-copper amalgams.

### Legends for Figures

Figure 1. Typical fractional stress-loss curves. Experimental temperature was 37C. (A)  $D_t/S_o$  versus time; and (B)  $D_t/S_o$  versus  $\ln(\text{time} + 1)$ .

Figure 2. Relative relaxation rates of seven high copper amalgam alloys. Curves are best-fit approximations.

## References

1. Mahler, D. B.; Terkla, L. G.; Van Eysden, J.; and Reisbick, M. H.: Marginal Fracture vs Mechanical Properties of Amalgam, J Dent Res 49: 1452-1457, 1973.
2. Osborne, J. W.; Phillips, R. W.; Norman, R. D.; and Swartz, M. L.: Static Creep of Certain Commercial Amalgam Alloys, JADA 89:620-622, 1974.
3. Eames, W. B.; and Mac Namara, J. F.: Eight High-Copper Amalgam Alloys and Six Conventional Alloys Compared, J Operative Dentistry 3:98-107, 1976.
4. Paddon, J. M.; and Wilson, A. D.: Stress Relaxation Studies on Amalgam, J Dent Res 54:427, 1975.
5. Huget, E. F.; de Simon, L. B.; and Hertert, R. S.: Stress Relaxation of Dental Amalgam Alloys, J Biomed Mater Res, In press.
6. Guide to Dental Materials and Devices, 6th ed, Chicago: American Dental Association 1972-1973, pp 168-171.

TABLE 1

STRESS-LOSSES AT 60 SECONDS ( $D_t/S_o/60$ ) FOR  
HIGH-COPPER AMALGAM ALLOYS

Alloy	Temperature, C							
	0	10	20	30	37	43	48	55
	%	%	%	%	%	%	%	%
A	5(1)*	7(1)*	10(1)*	10(2)*	12(4)*	13(2)*	15(3)*	21(2)*
B	6(2)	9(3)	13(3)	15(5)	20(2)	23(2)	34(2)	34(3)
C	8(2)	10(2)	13(2)	17(3)	19(3)	28(2)	37(6)	44(5)
D	6(1)	7(1)	9(4)	13(1)	13(1)	16(2)	24(2)	34(3)
E	10(1)	13(2)	17(1)	26(2)	36(4)	42(3)	46(4)	56(3)
F	9(2)	11(3)	18(1)	20(1)	28(1)	26(3)	34(4)	31(5)
G	7(2)	11(2)	12(2)	15(1)	17(3)	24(3)	26(3)	30(3)

\* Standard deviation in parentheses.

## Appendix

### HIGH-COPPER AMALGAM ALLOYS: PORTIONING AND TRITURATION

Alloy	Mercury-Alloy Portions mg Hg : mg Alloy	Trituration Time seconds
A <sup>*</sup>	286 : 350	25
B (pellet)	325 : 396	15
C <sup>*</sup>	388 : 388	20
D <sup>*</sup>	315 : 375	15
E (pellet)	459 : 390	20
F <sup>*</sup>	710 : 710	17
G (powder)	700 : 700	17

\* Precapsulated mercury and alloy.

